



啓盟工業股份有限公司
CHI MENG INDUSTRY CO.,LTD.

PE/EVA 發泡, C 系列產品物性表
PE/EVA Foam, C SERIES PHYSICAL PROPERTIES

項目 Items 品名 Articles	硬度 Hardness <i>ASTM D2240</i> SHORE C SHORE 00		延伸率 Elongation Ratio <i>ASTM D412</i> (%) ↑	抗張強度 Tensile Strength <i>ASTM D412</i> (kPa) ↑	撕裂強度 Tear Strength <i>ASTM D624</i> (kN/m) ↑	25%壓縮應力 Compression Strength 25% <i>ASTM D1056</i> (kPa) ↑	25%壓縮變型 Compression Set 25% <i>ASTM D1056</i> (%) ↓	密度 Density <i>ASTM D3575</i> (kg/m ³)	規格 Standard Size (mm)	備註 Note	
C-3000	11±3	20~40	300	200	1.2	20	35.0	27±5	1000*2000*87 1000*2000*100		
C-2000	13±3	25~40	150	300	1.5	25	32.0	30±5	1000*2000*100		
C-1800	18±4	35~55	200	350	2.2	40	32.0	40±5	1000*2000*87		
C-1207 ²⁷	28±4	45~65	150	300	1.8	45	24.0	45±5	1200*2400*75		
C-1207 ³⁵	36±4	55~70	150	400	2.0	60	24.0	55±5	1120*2050*75		
C-1206	41±4	55~75	150	500	2.9	90	24.0	60±5	920*2100*75		
C-1206EV	32±4	45~65	100	400	2.0	70	24.0	60±5	1000*2000*75		
C-1000B	32±3	50~65	100	800	3.5	80	20.0	75±5	1200*2400*43		
C-0800	42±4	55~70	100	1000	4.5	90	20.0	90±5	1000*2000*43		
C-0600	47±4	60~75	120	1200	6.5	100	16.0	100±10	1200*2400*43		
C-0400	62±4	70~85	120	1600	10.0	140	12.0	120±10	1150*2150*30		
2025.01.20											

本表所提供之數值皆為代表值，並非保證值。

All given data should be considered as a guide, but can not be regarded as an engagement from our side.

www.chimeng.com.tw

sales@chimeng.com.tw