



啓盟工業股份有限公司
CHI MENG INDUSTRY CO.,LTD.

PE/EVA 發泡, H, PE 系列產品物性表
PE/EVA Foam, H, PE SERIES PHYSICAL PROPERTIES

項目 Items 品名 Articles	硬度 Hardness <i>ASTM D2240</i> SHORE C SHORE 00		延伸率 Elongation Ratio <i>ASTM D412</i> (%) ↑	抗張強度 Tensile Strength <i>ASTM D412</i> (kPa) ↑	撕裂強度 Tear Strength <i>ASTM D624</i> (kN/m) ↑	25%壓縮應力 Compression Strength 25% <i>ASTM D1056</i> (kPa) ↑	25%壓縮變型 Compression Set 25% <i>ASTM D1056</i> (%) ↓	密度 Density <i>ASTM D3575</i> (kg/m ³)	規格 Standard Size (mm)	備註 Note	
H-2500NN	17±3	30~50	200	200	1.5	30	32.0	27±3	1000*2000*100	UL94 HF1, ★	☹
H-2500	17±3	30~50	170	200	1.5	30	32.0	27±3	1000*2000*100		
H-1800	28±4	45~65	150	350	1.8	55	32.0	40±5	1000*2000*87		
									1120*2100*87		
									1180*2100*73		
PE-0901	72±3	70~90	100	2200	10.0		24.0	90±10	1700*1150*42		
PE-1301	75±3	75~95	100	3200	12.0		24.0	100±10	1050*1450*32		
★：無鹵, Halogen Free. ☹：耐燃產品, Fire Retardant.											
										2025.01.20	

本表所提供之數值皆為代表值，並非保證值。

All given data should be considered as a guide, but can not be regarded as an engagement from our side.

www.chimeng.com.tw

sales@chimeng.com.tw