



啓盟工業股份有限公司
CHI MENG INDUSTRY CO.,LTD.

橡膠發泡, EPDM 系列產品物性表
Rubber Foam, EPDM SERIES PHYSICAL PROPERTIES

項目 Items 品名 Articles	硬度 Hardness <i>ASTM D2240</i> SHORE C SHORE 00		延伸率 Elongation Ratio <i>ASTM D412</i> (%) ↑	抗張強度 Tensile Strength <i>ASTM D412</i> (kPa) ↑	撕裂強度 Tear Strength <i>ASTM D624</i> (kN/m) ↑	25%壓縮應力 Compression Strength 25% <i>ASTM D1056</i> (kPa) ↑	25%壓縮變型 Compression Set 25% <i>ASTM D1056</i> (%) ↓	密度 Density <i>ASTM D3575</i> (kg/m ³)	規格 Standard Size (mm)	備註 Note		
	EPDM-0700	13±3	25~40	150	320	2.0	20	48.0	80±10	1000*2000*53 1400*2000*53	Sulfur Free 無硫	
	EPDM-0650	11±3	20~35	200	350	2.2	20	48.0	120±20	1000*2000*53		
EPDM-0500	18±4	35~50	150	450	2.7	35	40.0	120±20	1000*1500*53 1000*2000*53 1000*2000*65 1400*1500*53 1400*2000*53			
EPDM-0400LD	24±4	40~60	180	480	2.5	45	32.0	140±15	1000*2000*53 1000*2000*65			
EPDM-0400	24±4	40~60	200	550	3.4	45	32.0	160±30	1000*2000*53			
EPDM-0350	26±4	42~62	220	580	3.6	50	25.0	175±30	1000*2000*53			
EPDM-0300	28±4	45~65	250	600	3.9	55	20.0	200±30	1000*2000*53			
EPDM-0250	32±4	50-70	180	700	4.2	75	15.0	220±40	1000*1750*53			
2025.01.20												

本表所提供之數值皆為代表值，並非保證值。

All given data should be considered as a guide, but can not be regarded as an engagement from our side.

www.chimeng.com.tw

sales@chimeng.com.tw