



啓盟工業股份有限公司
CHI MENG INDUSTRY CO.,LTD.

導電發泡, LCX 系列產品物性表
Conductive Foam, LCX SERIES PHYSICAL PROPERTIES

項目 Items 品名 Articles	硬度		延伸率	抗張強度	撕裂強度	25%壓縮應力	25%壓縮變型	密度	表面阻抗	規格	備註	
	Hardness		Elongation Ratio	Tensile Strength	Tear Strength	Compression Strength 25%	Compression Set 25%	Density	Surface Resistivity	Standard Size	Note	
	ASTM D2240		ASTM D412	ASTM D412	ASTM D624	ASTM D1056	ASTM D1056	ASTM D3575	ASTM D257			
	SHORE C	SHORE 00	(%) ↑	(kPa) ↑	(kN/m) ↑	(kPa) ↑	(%) ↓	(kg/m³)	Ω	(mm)		
LCX-200#2	24±4	40~60	49	320	1.4	70	8.0	50±5	10 ⁴ ~10 ⁶	1000*2000*80		
LCX-150	45±5	60~80	44	410	1.8	110	11.2	60±5	10 ⁴ ~10 ⁶	1000*1000*75		
2025.01.20												

本表所提供之數值皆為代表值，並非保證值。

All given data should be considered as a guide, but can not be regarded as an engagement from our side.

www.chimeng.com.tw
sales@chimeng.com.tw