



啓盟工業股份有限公司
CHI MENG INDUSTRY CO.,LTD.

吸震材發泡, SA 系列產品物性表
Shock Absorption Foam, SA SERIES PHYSICAL PROPERTIES

項目 Items 品名 Articles	硬度 Hardness <i>ASTM D2240</i> SHORE C SHORE 00		延伸率 Elongation Ratio <i>ASTM D412</i> (%) ↑	抗張強度 Tensile Strength <i>ASTM D412</i> (kPa) ↑	撕裂強度 Tear Strength <i>ASTM D624</i> (kN/m) ↑	25%壓縮應力 Compression Strength 25% <i>ASTM D1056</i> (kPa) ↑	25%壓縮變型 Compression Set 25% <i>ASTM D1056</i> (%) ↓	密度 Density <i>ASTM D3575</i> (kg/m ³)	反撥彈性 Rebound Resilience <i>ASTM D2632</i> %	規格 Standard Size (mm)	備註 Note	
SA-12	30±4	50~70	200	400	2.0	45	18.0	55±5	30	1000*2000*75		
SA-10	20±4	35~55	300	800	2.5	45	15.0	60±5	20	1000*2000*53		
SA-06	27±4	45~65	300	1600	6.9	50	10.0	100±10	8	900*2000*40		
2025.01.20												

本表所提供之數值皆為代表值，並非保證值。

All given data should be considered as a guide, but can not be regarded as an engagement from our side.

www.chimeng.com.tw

sales@chimeng.com.tw