



啓盟工業股份有限公司
CHI MENG INDUSTRY CO.,LTD.

特殊發泡, Melamine & Zotofoams產品物性表
Specialty Foam, BASF Melamine & Zotofoams SERIES PHYSICAL PROPERTIES

項目 Items 品名 Articles	硬度		延伸率	抗張強度	撕裂強度	25%壓縮應力	25%壓縮變型	密度	規格	備註
	Hardness		Elongation Ratio	Tensile Strength	Tear Strength	Compression Strength 25%	Compression Set 25%	Density	Standard Size	Note
	ASTM D2240		ASTM D412	ASTM D412	ASTM D624	ASTM D1056	ASTM D1056	ASTM D3575		
	SHORE C	SHORE 00	(%) ↑	(kPa) ↑	(kN/m) ↑	(kPa) ↑	(%) ↓	(kg/m³)	(mm)	
Zotefoams, LD-4	24±4	40~55	150	600	10.3	50	22	45±5	1000*2000*30	氮氣 · Nitrogen.
2025.01.20										

本表所提供之數值皆為代表值，並非保證值。

All given data should be considered as a guide, but can not be regarded as an engagement from our side.

www.chimeng.com.tw

sales@chimeng.com.tw